

## Vikoflex®

Epoxidized oils, esters: PVC plasticization, stabilization, acid scavenging.

Trade Name	Identity	Minimum Oxirane	Viscosity
Vikoflex 7170	Epoxidized Soybean Oil	7.0%	3.8 s
Vikoflex 7190	Epoxidized Linseed Oil	9.0%	8.0 s
Vikoflex 4050	Epoxidized Octyl Soyate	5.3%	40 cps
Vikoflex 5075	Epoxidized PGDO	4.4%	1.2 s
Vikoflex 7010	Methyl Epoxy Soyate	6.7%	30 cps
Vikoflex 7040	Butyl Epoxy Soyate	6.3%	40 cps
Vikoflex 7080	Epoxidized Octyl Soyate	5.3%	40 cps
Vikoflex 9010	Methyl Epoxy Linseedate	9.0%	40 cps
Vikoflex 9040	Butyl Epoxy Linseedate	8.0%	45 cps
Vikoflex 9080	Octyl Epoxy Linseedate	7.0%	45 cps


## Vikolox®

Epoxidized Alpha Olefins: Lube additives, adhesives, coatings, sealants, personal care, surfactants, Polyol modifiers, epoxy reactive diluents.

Trade Name	Formula	Minimum Oxirane
Vikolox 10	C <sub>10</sub> H <sub>20</sub> O	9.0%
Vikolox 12	C <sub>12</sub> H <sub>24</sub> O	7.8%
Vikolox 14	C <sub>14</sub> H <sub>28</sub> O	6.8%
Vikolox 16	C <sub>16</sub> H <sub>32</sub> O	6.0%
Vikolox 18	C <sub>18</sub> H <sub>36</sub> O	5.4%
Vikolox 20-24	C <sub>20-24</sub> H <sub>40-48</sub> O	4.4%
Vikolox 24-28	C <sub>24-28</sub> H <sub>48-56</sub> O	3.25%
Vikolox 30+	C <sub>30+</sub> H <sub>60</sub> O	2.25%

**Note:** Each Vikolox can be converted to the resultant Vikinol® or 1,2 glycol.

## Specialty Epoxides – Custom Epoxidation Services



### Important Notice Regarding This Information

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be taken as an inducement to infringe any patent and the user is advised to take appropriate steps to be assured that and proposed use of the product will not result in patent infringement.

**Note:** The "Material Safety Data Sheet" on this product is available on request from the Safety and Environmental Services Department of Arkema Inc., 2000 Market Street, Philadelphia, PA 19103.

## Epoxidized Oleyl Alcohol Terpene Oxides

- Alpha Pinene Oxide and Campholenic Aldehyde - fragrances
- Limonene Monoxide and Dioxide - reactive epoxy diluents

## Environmental and Safety Information

BEFORE HANDLING THIS MATERIAL, READ AND UNDERSTAND THE MSDS (MATERIAL SAFETY DATA SHEET) FOR ADDITIONAL INFORMATION ON PERSONAL PROTECTIVE EQUIPMENT AND FOR SAFETY, HEALTH AND ENVIRONMENTAL INFORMATION.

For Environmental, Safety & Toxicology information, contact our Customer Service Department at (800) 446-2800 to request a Material Safety Data Sheet. Arkema believes strongly in Responsible Care as a Public Commitment.

## For Product and Technical Information Contact

Chuck Castley  
Global Market Manager Epoxides  
(856) 223-9829 (phone)  
(856) 223-5492 (fax)  
www.additives-arkema.com (website)  
chuck.castley@arkemagroup.com (e-mail)

## For Order Information Contact

Arkema Inc.  
2000 Market Street, Philadelphia, PA 19103-3222  
(800) 446-2800 (phone)  
(215) 419-7875 (fax)  
arkema.usph-additives-cs@arkemagroup.com (e-mail)

## Visit Us at Our Website

[www.additives-arkema.com](http://www.additives-arkema.com)

Vikoflex is a registered trademark of Arkema Inc.



Arkema Inc.  
2000 Market Street  
Philadelphia, PA 19103  
Customer Service 1.800.446.2800

[www.additives-arkema.com](http://www.additives-arkema.com)