



Luperox® MC

A Unique Organic Peroxide for
Curing SMC and BMC Formulations



ARKEMA

Luperox® MC* organic peroxide from Arkema Inc. is offered specifically to fabricators of sheet molding compounds (SMC) and bulk molding compounds (BMC) in North America. It is designed to cure the several hundred million pounds of SMC and BMC formulations used annually to make automotive body panels and structural parts, door skins, electrical boxes, satellite dishes, bath fixtures (shower stalls, bath tubs, etc.), personal water craft, and appliance housings.

When used to cure SMC and BMC formulations, it solves problems such as non-fill, dull surface, edge chips, knit lines, pregel, and undercure. In addition, it improves production cycle times.

Luperox® MC organic peroxide is a room-temperature-stable, liquid, organic peroxide having a unique formulation resulting from the manufacturing process. Some of its properties are listed here:

Appearance:Colorless-to-pale-yellow,
clear liquid
Specific Gravity:.....0.9308 @20°C
Melting/Freezing Point:Below - 78-C
10-Hour Half-Life Temperature:98°C (solvent)
Recommended
Storage Temperature:Below 30°C
Maximum Allowed
Storage Temperature:38°C
Flash Point:64°C
SADT:.....65°C (35 lb container)
Stability:1.8% Assay Loss
(After 4 weeks at 40°C)
Active Oxygen Content:5.56% minimum

Luperox® MC organic peroxide is very efficient, providing shorter gel-to-cure-times compared to other room-temperature- stable peroxyesters currently used in SMC and BMC applications. The following table shows a comparison of Luperox® MC organic peroxide with other well-known initiators on an equal weight basis in the same resin formulation. Cure characteristics were measured dielectrically using a Micromet instrument to gather cure data at 300°F.



Curing Data	LUPEROX® MC	t-Butyl Peroxybenzoate, Luperox® P, 99%	00-(t-Butyl) 0-(2-Ethylhexyl) Monoperoxycarbonate Luperox® TBEC, 96%	00-(t-Butyl) 0-Isopropyl Monoperoxycarbonate Luperox® TBIC, M7S*	t-Amyl Peroxybenzoate Technically Pure Luperox® TAP, 95%	t-Butyl Peroxyacetate Luperox® 7M75*
Gel Time (sec)	14.4±0.8	16.0±0.6	17.3±0.8	12.8±0.6	12.9±1.3	14.2±0.3
80% Cure Time (sec)	20.2±0.0	31.8±0.5	27.5±0.4	24.0±0.6	25.8±0.5	29.4±1.8
Cure Time (sec)	25.9±0.2	40.8±0.3	35.1±0.5	31.0±0.5	33.3±0.4	37.7±1.6
Gel-to Cure Time (sec)	11.5±0.8	24.8±0.7	17.8±0.9	18.2±0.8	20.4±1.4	23.5±1.6
Max Cure Temp (°F)	302.4±0.1	301.8±0.4	301.4±0.4	302.6±0.2	300.1±0.7	301.0±0.9
Gel Time/ Cure Time	0.56±0.03	0.39±0.01	0.49±0.02	0.41±0.02	0.39±0.04	0.38±0.02

*75% in odorless mineral spirits
Initiators were compared on an equal weight basis, 2.35 phr, in a typical commercial SMC formulation.



ARKEMA Inc. is committed to the American Chemistry Council's
Responsible Care and Product Stewardship Initiatives.

R E S P O N S I B L E C A R E ®

V I S I T U S A T
W W W . L U P E R O X . C O M

© 2006 Arkema Inc. All rights reserved.

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be assured that any proposed use of the product will not result in patent infringement.

See MSDS For Health And Safety Considerations.

Luperox® is a registered trademark of Arkema Inc.

Responsible Care® is a registered trademark of the American Chemistry Council.

*Luperox® MC is covered in US 6,617,388B2



ARKEMA INC.

2000 Market Street, Philadelphia, Pa 19103-3222

Phone: 1-800-558-5575 • Fax: 215-419-7413

www.Arkemainc.com